

标称直径 Nominal Dirmeter		抗拉强度 Tensile strength				伸长率最小值%10英寸（250mm） Elongation min% in 10 in. (or 250mm)	
英寸 In	mm	H等级最小值 Minimun of H classes		A等级最大值 Maximun of A classes		H等级 H class	A等级 A class
		Ksi	Mpa	Ksi	Mpa		
0.0349	8.252	16	110	20	138	1.5	15
0.2893	7.348	16	110	20	138	1.5	15
0.2576	6.543	18	124	20	138	1.5	15
0.2294	5.827	20	138	20	138	1.5	15
0.2043	5.189	22	152	20	138	1.5	15
0.1819	4.620	23	159	20	138	1.5	15
0.1620	4.115	24	166	20	138	1.5	15
0.1443	3.665	25	172	20	138	1.5	15
0.1285	3.264	26	179	20	138	1.0	15
0.1144	2.906	27	186	20	138	1.0	15
0.1019	2.588	28	193	20	138	1.0	15
0.0907	2.300	29	200	20	138	1.0	15
0.0808	2.05	30	207	20	138	1.0	15
0.0720	1.83	30	207	20	138	1.0	15
0.0641	1.63	30	207	20	138	1.0	15
0.0571	1.45	30	207	20	138	1.0	15
0.0508	1.29	30	207	20	138	1.0	15
0.0453	1.15	30	207	20	138	1.0	15
0.0403	1.02	30	207	20	138	1.0	15
0.0359	0.912	30	207	20	138	1.0	15
0.0320	0.813	30	207	20	138	1.0	15
0.0285	0.724	30	207	20	138	1.0	15
0.0253	0.643	30	207	20	138	1.0	15
0.0226	0.574	30	207	25	172	1.0	10
0.0201	0.511	30	207	25	172	1.0	10
0.0179	0.455	30	207	25	172	1.0	10
0.0159	0.404	30	207	25	172	1.0	10
0.0142	0.361	30	207	25	172	1.0	10
0.0126	0.320	30	207	25	172	1.0	5
0.0113	0.287	30	207	25	172	1.0	5
0.0100	0.254	30	207	25	172	1.0	5
0.0089	0.226	30	207	25	172	1.0	5
0.0080	0.203	30	207	25	172	1.0	5
0.0071	0.180	30	207	25	172	1.0	5
0.0063	0.160	30	207	25	172	1.0	5
0.0058	0.142	30	207	25	172	1.0	5
0.0050	0.127	30	207	25	172	1.0	5

注:H为硬态,A为软态 H--Hard drawn,A--Annealed